

CE0473

Maximum Cure® CHEMICAL CURE SEALANT SYSTEM CONTAINS FLUORIDE

9/13

INDICATIONS FOR USE: Maximum Cure® Sealants are intended for use in direct and indirect bonding of brackets and appliances.

INSTRUCTION FOR USE:

1. Thoroughly prophylax the tooth surface with a paste which does not contain oil. Rinse and dry.
2. Acid etch each tooth for 30 seconds.
3. Rinse the acid from each tooth for 5 seconds and dry with oil-free air.
NOTE: If the enamel is atypical, Enhance™ Adhesion Booster or Assure® Universal Bonding Resin can be applied at this point.
4. On a mixing pad, place 1 drop each of Maximum Cure® Sealant A & B.
5. Immediately mix with a brush or sponge pellet.
6. Apply the mixed sealant to the etched enamel surface. The aforementioned mix ratio will produce a 1-1/2 minute working time from the start of mix. To extend the working time to 3-1/2 minutes, mix on a paper covered frozen slab.
7. Proceed with the application of any two paste or light cure bonding paste to each bracket or appliance. Brackets and appliances can be placed before the sealant totally sets without interference to the sealant or bonding paste. If utilizing a light cure paste, wait 3 minutes prior to seating a bracket.

INSTRUCTIONS FOR USE WITH CUSTOM BASE INDIRECT BONDING PROCEDURE

1. After preparing the enamel as described above, the operator has 2 choices for use as an indirect adhesive:
 - A.) Mix Maximum Cure part A & B and apply a thin coat to the enamel. Then, apply a slightly thicker coat to each custom pad and immediately seat tray.
 - OR
 - B.) Apply a moderate coat of Maximum Cure part A to the custom pad and part B to the enamel. Proceed to seat the tray.
- In either case, hold the tray for 90 seconds and wait 5 minutes before removing tray from mouth.

NOTE: The caps should always be replaced immediately after use. Maximum Cure® Sealant is available in two sizes: 7g Part A 7g Part B, or 20g Part A and 20g Part B. Maximum Cure® Filled Sealant is available in the 7g size only. Phase II® and Excel® kits can be ordered with Maximum Cure® Sealant in a place of the conventional sealant at no extra charge. Simply specify.



PRECAUTIONS: Unpolymerized resins may cause skin sensation in susceptible persons. In case of contact with the skin, wash thoroughly with soap and water. If accidentally instilled into eye, flush with copious amounts of water and seek medical attention immediately. Contact with other tissues: rinse spill area immediately with copious amounts of water for several minutes.



Flammable



TEMPERATURE LIMITATION: Store refrigerated (36-46-degrees F.) Avoid excessive heat. Allow to reach room temperature prior to use.

TO REORDER: Regular: Ref# MC7AF 7g Part A, Ref# MC7B 7g Part B, Ref# MC20AF 20g Part A, Ref# MC20B 20g Part B

Filled: Ref# MCF7AF 7g Filled Part A, Ref# MCF7B 7g Filled Part B,

WARRANTY: Reliance Orthodontics Products, Inc. recognizes its responsibility to replace products if proven to be defective. Reliance Orthodontics Products, Inc. does not accept liability for any damages or loss, either direct or consequential, stemming from the use of or inability to use the products as described. Before using, it is the responsibility of the user to determine the suitability of the product for its intended use. The user assumes all risk and liability in connection therewith.

Rx Only: U.S. Federal law restricts this device to sale by or on the order of a dental professional.



Reliance Orthodontic Products, Inc.

1540 West Thorndale Ave. • Itasca, Illinois 60143 U.S.A.
Call Toll Free: 1-800-323-4348 • Phone: (630) 773-3580
Fax: (630) 250-7704 • Web: www.relianceorthodontics.com
Copyright © 1987 by Reliance Orthodontic Products, Inc.
All rights reserved. Made in the USA.
EMERGO EUROPE
Molensmatt 11
2513 BR, The Hague
The Netherlands

EC REP

Australian Sponsor: Emergo
Australia
201 Sussex St. Darling Park
Tower II, Level 20,
Sydney, NSW 2000 Australia

Scan for more information

CE0473

Maximum Cure® CHEMICAL CURE SEALANT SYSTEM CONTAINS FLUORIDE

9/13

INDICATIONS FOR USE: Maximum Cure® Sealants are intended for use in direct and indirect bonding of brackets and appliances.

INSTRUCTION FOR USE:

1. Thoroughly prophylax the tooth surface with a paste which does not contain oil. Rinse and dry.
2. Acid etch each tooth for 30 seconds.
3. Rinse the acid from each tooth for 5 seconds and dry with oil-free air.
NOTE: If the enamel is atypical, Enhance™ Adhesion Booster or Assure® Universal Bonding Resin can be applied at this point.
4. On a mixing pad, place 1 drop each of Maximum Cure® Sealant A & B.
5. Immediately mix with a brush or sponge pellet.
6. Apply the mixed sealant to the etched enamel surface. The aforementioned mix ratio will produce a 1-1/2 minute working time from the start of mix. To extend the working time to 3-1/2 minutes, mix on a paper covered frozen slab.
7. Proceed with the application of any two paste or light cure bonding paste to each bracket or appliance. Brackets and appliances can be placed before the sealant totally sets without interference to the sealant or bonding paste. If utilizing a light cure paste, wait 3 minutes prior to seating a bracket.

INSTRUCTIONS FOR USE WITH CUSTOM BASE INDIRECT BONDING PROCEDURE

1. After preparing the enamel as described above, the operator has 2 choices for use as an indirect adhesive:
 - A.) Mix Maximum Cure part A & B and apply a thin coat to the enamel. Then, apply a slightly thicker coat to each custom pad and immediately seat tray.
 - OR
 - B.) Apply a moderate coat of Maximum Cure part A to the custom pad and part B to the enamel. Proceed to seat the tray.
- In either case, hold the tray for 90 seconds and wait 5 minutes before removing tray from mouth.

NOTE: The caps should always be replaced immediately after use. Maximum Cure® Sealant is available in two sizes: 7g Part A 7g Part B, or 20g Part A and 20g Part B. Maximum Cure® Filled Sealant is available in the 7g size only. Phase II® and Excel® kits can be ordered with Maximum Cure® Sealant in a place of the conventional sealant at no extra charge. Simply specify.



PRECAUTIONS: Unpolymerized resins may cause skin sensation in susceptible persons. In case of contact with the skin, wash thoroughly with soap and water. If accidentally instilled into eye, flush with copious amounts of water and seek medical attention immediately. Contact with other tissues: rinse spill area immediately with copious amounts of water for several minutes.



Flammable



TEMPERATURE LIMITATION: Store refrigerated (36-46-degrees F.) Avoid excessive heat. Allow to reach room temperature prior to use.

TO REORDER: Regular: Ref# MC7AF 7g Part A, Ref# MC7B 7g Part B, Ref# MC20AF 20g Part A, Ref# MC20B 20g Part B

Filled: Ref# MCF7AF 7g Filled Part A, Ref# MCF7B 7g Filled Part B,

WARRANTY: Reliance Orthodontics Products, Inc. recognizes its responsibility to replace products if proven to be defective. Reliance Orthodontics Products, Inc. does not accept liability for any damages or loss, either direct or consequential, stemming from the use of or inability to use the products as described. Before using, it is the responsibility of the user to determine the suitability of the product for its intended use. The user assumes all risk and liability in connection therewith.

Rx Only: U.S. Federal law restricts this device to sale by or on the order of a dental professional.



Reliance Orthodontic Products, Inc.

1540 West Thorndale Ave. • Itasca, Illinois 60143 U.S.A.
Call Toll Free: 1-800-323-4348 • Phone: (630) 773-3580
Fax: (630) 250-7704 • Web: www.relianceorthodontics.com
Copyright © 1987 by Reliance Orthodontic Products, Inc.
All rights reserved. Made in the USA.
EMERGO EUROPE
Molensmatt 11
2513 BR, The Hague
The Netherlands

EC REP

Australian Sponsor: Emergo
Australia
201 Sussex St. Darling Park
Tower II, Level 20,
Sydney, NSW 2000 Australia

Scan for more information